



Pink Rose

PIGMENTS PVT. LTD.



PIGMENT FOR PAINT

Pigment for Paint • Yellow & Orange

YELLOW & ORANGE SHADES

Product Code	Pigment / Colour Index	SG	Oil Abs.	Light	Weather	Water	EtOH	Xylene	Heat
Yellow 303	PY 1	1.40	≤45	6–7	4–5	3	2	5	160
Yellow 306	PY 2	1.40	≤45	6–7	4	4	3	5	160
Yellow 309	PY 3	1.35	≤40	5	4	3	2	4–5	160
Yellow 3361	PY 12	1.40	≤50	4–5	3	3	2	4–5	180
Yellow 3195	PY 65	1.40	≤50	7	6	4	3	5	160
Yellow 3221	PY 74 (2GX)	1.40	≤45	7	5–6	4	2	4–5	180
Yellow 3225	PY 74 (5GX)	1.40	≤45	6–7	5–6	4	2	4–5	180
Yellow 3249	PY 83	1.55	≤45	7	5–6	4	3	4–5	200
Yellow 3251C	PY 83	1.55	<50	7–8	6	4	3	5	200
Yellow 3414	PY 138	1.75	<40	7–8	7	5	4	5	250
Yellow 3417	PY 139	1.60	<50	7–8	7	5	4	5	240
Yellow 3453	PY 151	1.60	<50	7–8	6–7	5	4	5	250
Yellow 3462	PY 154	1.65	≤55	8	6–7	5	4	5	250
Orange 735	PO 5	1.40	<40	7	6	4	3	5	160
Orange 791	PO 13	1.45	<45	6–7	5–6	3	2	5	160
Orange 7238	PO 34	1.45	≤45	7	5–6	4	3	5	200
Orange 7252	PO 36	1.40	≤40	8	7	5	4	5	280
Orange 7448	PO 64	1.50	≤60	8	7	5	4	5	280

Performance values reproduced from the supplied reference. Confirm suitability for the intended rubber compound and process.

Pigment for Paint • Red Series

RED SHADES

Product Code	Pigment / Colour Index	SG	Oil Abs.	Light	Weather	Water	EtOH	Xylene	Heat
Red 515	PR 3	1.40	≤50	7	4–5	3	2	5	180
Red 516	PR 3	1.40	≤50	7	4–5	3	2	5	180
Red 520	PR 4	1.45	≤45	6	5	3	2	3	160
Red 525	PR 5	1.45	≤45	5–6	4–5	3	2	4–5	160
Red 540	PR 8	1.50	≤50	5–6	4	3	2	4	180
Red 560	PR 12	1.50	≤55	6	3	3	2	4	160
Red 5242	PR 48.2	1.70	<50	5–6	3–4	3	2	3	200
Red 5248	PR 48.4	1.70	<50	6–7	5–6	4	3	4	200
Red 5285C	PR 57.1	1.50	<55	5	3	3	2	3	200
Red 5315	PR 63.1	1.50	≤50	6	4–5	3	2	3	160
Red 5561	PR 112	1.50	≤40	7	6	3	2	5	200
Red 5562	PR 112	1.50	≤40	7	6	3	2	5	200
Red 5564	PR 112	1.50	≤40	7	6	3	2	5	200
Red 5610	PR 122	1.50	≤50	7–8	7	5	4	5	280
Red 5730	PR 146	1.40	≤50	6	5	3	2	5	180
Red 5850	PR 170	1.45	≤50	7	6	2	3	5	260
Red 5851	PR 170	1.50	≤50	7	6	4	3	5	260
Red 5940	PR 188	1.50	≤50	7	4	3	3	5	200
Red 51270	PR 254	1.40	≤50	4	3–5	5	5	5	300

Performance values reproduced from the supplied reference. Confirm suitability for the intended rubber compound and process.

Pigment for Paint • Extended Range

EXTENDED RANGE

Product Code	Pigment / Colour Index	SG	Oil Abs.	Light	Weather	Water	EtOH	Xylene	Heat
Green 107	PG 7	2.10	≤45	8	7	5	4–5	5	280
Green 108	PG 8	1.50	≤45	6	5	3	2	5	180
Blue 9150	PB 15.0	1.60	≤45	8	7	5	4	4–5	220
Blue 9152	PB 15.2	1.60	≤50	8	7	5	4	5	220
Blue 9153	PB 15.3	1.60	≤50	8	7	5	4	5	280
Blue 9261	PB 29	5.60	≤30	4	3–4	4	3	4	230
Violet 1119	PV 19	1.65	≤50	8	7	5	4	5	280
Violet 1123	PV 23	1.40	≤50	7	6	5	4	5	260
Violet 1124	PV 23	1.40	≤50	7	6	5	4	5	260
Lemon Yellow 2222	PY 34	5.50	≤25	7–8	6–7	5	4	4–5	220
Middle Yellow 2222	PY 34	5.50	≤25	7–8	6–7	5	4	4–5	220
Orange 4245	PR 104	5.50	≤25	7–8	6–7	5	4	4–5	230
Yellow NM	Organic Chrome Yell...	1.50	≤45	6–7	5–6	4	3	4	160
Yellow MV	Organic Middle Chro...	1.50	≤50	6–7	5–6	4	3	4	160
Scarlet JP	Organic Scarlet Chr...	1.50	≤45	6–7	5–6	4	3	4	160

Performance values reproduced from the supplied reference. Confirm suitability for the intended rubber compound and process.



PINK ROSE PIGMENTS PVT. LTD.

PAINT PIGMENT SOLUTIONS



115, Narayan Arcade, Shahwadi Bus Stand, Narol, Ahmedabad-382405 (INDIA)



098250 38757



pinkrosepigment@gmail.com
exports@pinkrosepigments.com
sales@pinkrosepigments.com



www.pinkrosepigments.com

PAINT PIGMENT SOLUTIONS

QUALITY | CONSISTENCY | PERFORMANCE